

PCT


WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 : <b>B29C 55/24, 55/26, 47/90, 47/92 // B29L 23:00, B29K 101:12</b>		A1	(11) International Publication Number: <b>WO 97/06940</b>
			(43) International Publication Date: 27 February 1997 (27.02.97)
(21) International Application Number: PCT/AU96/00514		(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 16 August 1996 (16.08.96)		Published With international search report.	
(30) Priority Data: PN 4850 18 August 1995 (18.08.95) AU			
(71) Applicants (for all designated States except US): VINIDEX TUBEMAKERS PTY. LIMITED [AU/AU]; 15 Merriwa Street, Gordon, NSW 2072 (AU). UPONOR B.V. [NL/NL]; Hoeksema 6-8, NL-1002 BR Amsterdam (NL).			
(72) Inventors; and (75) Inventors/Applicants (for US only): CHAPMAN, Peter, Glanville [AU/AU]; 45 Ronald Avenue, Greenwich, NSW 2065 (AU). WALLACE, Allan, Kenneth [AU/AU]; 31a Birkinshaw Avenue, Tranmere, S.A. 5073 (AU).			
(74) Agents: HALFORD, Graham, William et al.; Halford & Co. Patent & Trade Mark Attorneys, 1 Market Street, Sydney, NSW 2000 (AU).			

(54) Title: CONTROL METHOD FOR THE MANUFACTURE OF ORIENTED PLASTICS TUBES



(57) Abstract

A method of expanding a tube of plastics material is disclosed in which a longitudinally travelling tube (10) is progressively diametrically expanded by internal fluid pressure in an expansion zone (20) between an upstream plug (24) and an expandable downstream plug (26). Expansion of the tube is controlled in response to parameters which directly or indirectly indicate variation in the relative velocity at which material is delivered to and removed from the expansion zone, such as detecting upstream tube velocity (38), early expansion diameter (36), axial force (39) on a sizing device (28) or the tube diameter (41) just before the expansion zone.

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

## CONTROL METHOD FOR THE MANUFACTURE OF ORIENTED PLASTICS TUBES

## BACKGROUND OF INVENTION

This invention relates to the manufacture of oriented plastics tubes, and in particular to the manufacture of tubes having a high degree of orientation in the circumferential direction.

5 International Patent Application No. WO 90/02644 describes a process for the manufacture of thermoplastics tubes for example for unplasticised polyvinyl chloride (uPVC) which have a degree of  
10 orientation in the circumferential direction that improves properties such as resistance to hoop stresses, and renders the tubes particularly suitable for transmission of water. The process described in that patent application comprises:

- 15 (i) extruding a tube of plastics material;
- (ii) temperature conditioning the extruded tube to bring it to a consistent temperature profile about the  
20 tube suitable for expansion of the tube to cause molecular orientation of the polymer, preferably to a temperature of 85-115°C for uPVC, more preferably 90-100°C.
- 25 (iii) diametrically expanding the tube by application of an internal pressure to the tube that is limited at its downstream end by a plug that is inflatable or otherwise expandable to maintain pressure within the expansion zone; and
- 30 (iv) cooling the expanded tube to set the tube in

-2-

its diametrically expanded configuration.

At the downstream end of the expansion zone the expanded tube passes through a circular passage in a sizing device which limits diametrical expansion of the tube to that which allows the expanded tube to slide through the sizing device. After the tube has passed through the expansion zone and while it is being cooled the tube may contract in diameter by a small amount, e.g. a few millimetres or less (so-called "snap-back") as the internal pressure is reduced, to give the tube its final, expanded, diameter.

In the case of tubes that are intended to be used as water pipes, and which must therefore be joined end-to-end, it is necessary for the diameter of the expanded tube, and especially its external diameter, to be controlled in order that the tube will be able to fit accurately and tightly within a coupling device or within an additionally expanded end section of an adjacent tube so as to prevent leakage. We have found, however, that control of the expansion process using conventional feedback control, i.e. by measuring the final expanded diameter and wall thickness of the tube, does not control the properties of the resultant tube sufficiently accurately, nor allow stable operation of the process itself.

### SUMMARY OF INVENTION

According to the present invention, there is provided a method of expanding a tube of plastics material in which a longitudinally travelling tube is progressively diametrically expanded by internal fluid pressure in an expansion zone between an upstream plug which fits closely within the bore of the

-3-

substantially unexpanded tube and a downstream plug which fits closely within the bore of the tube after the expansion step, wherein expansion of the tube is controlled in response to one or more parameters which directly or indirectly indicate variation in the relative velocity at which the material is delivered to and is removed from the expansion zone.

Control of the process in response to changes in the relative velocities is preferably achieved by varying the fluid pressure in the expansion zone. In one preferred form, this is done by controlling leakage of the expansion fluid past the expandable downstream plug, by varying the diameter of the expandable plug.

In the most preferred case in which the downstream plug is inflatable, the leakage is controlled by controlling the pressure of inflation fluid in the plug.

The variation in relative velocity into and out of the expansion zone is preferably measured indirectly, and may be measured by any one or more of the following methods:

(a) The absolute velocity of the unexpanded tube upstream of the expansion zone and the expanded tube downstream may be measured and compared. Preferably the upstream measurement is taken at a point substantially immediately before the expansion zone. This measurement will detect increases in expansion of the tube at the expansion zone as this will be accompanied by an increase in the velocity of material entering the expansion zone as the outward bulging will start to draw material from the upstream side of the upstream plug. In practice, the downstream velocity can be considered to be known with sufficient accuracy from the haul-off rate as no further stretch

-4-

occurs in the cooled section of pipe downstream of the expansion zone. Thus a reasonable approximation of the relative velocity can be determined by detecting the upstream velocity alone, and variations in the upstream velocity alone may be used as the control parameter as the haul-off rate is dictated by the downstream haul-off tractor and will not generally fluctuate other than due to deliberate change of the haul-off rate.

10

(b) The diameter of the partly expanded tube may be measured at a position within the expansion zone, preferably at a position less than about three times the pre-expansion tube diameter downstream of the upstream plug. This diameter reflects the precise configuration of the generally frusto-conical expansion region. For example, if the velocity of tube leaving the expansion zone reduces relative to the delivery to the expansion zone, the frusto-conical expansion region of the tube will bulge outwardly to some extent thereby increasing the measured diameter, while if velocity leaving the expansion zone increases relative to the delivery to the expansion zone, the frusto-conical expansion region will become more axially elongated and the measured diameter will decrease.

20

(c) The force exerted by the expanded tube on the sizing device in the axial direction may be measured. In a first mode of operation the tube expands to fit the sizing device and exerts an axial force on the sizing device in the downstream direction due to its shearing against the internal surface of the sizing device. The magnitude of the axial force will depend on the axial length over which the expanded tube contacts the sizing device and/or on the radial pressure which it applies to the device so that

30

35

-5-

appropriate feedback control can maintain the point at which the tube first contacts the sizing device at the set point. In a second mode of operation, the tube is slightly overexpanded before being drawn down in diameter through the sizing sleeve. The axial force on the sizing sleeve will reflect both the deformation of the overexpanded tube to enter the sizing device and shearing against the inner surface. In either operative mode the measured force is related to the shape of the expansion zone, and thus to the relative velocities as described above.

(d) The diameter of the unexpanded tube just prior to the expansion zone, for example less than about 10 times the pre-expansion tube diameter upstream of the upstream plug, may be measured. This reading reflects the long term average in velocity entering the expansion zone, as too high an entry velocity over a period of time will cause material to be drawn from the pre-expansion zone, resulting in thinning of the tube material and reduction of diameter upstream of the expansion zone.

#### BRIEF DESCRIPTION OF THE DRAWINGS

Further preferred embodiments shall now be described with reference to the accompanying drawings, in which:

Figure 1 is a schematic view of the tube manufacture and expansion process; and

Figures 2A and 2B are schematic details of the expanded tube entering the sizing sleeve in first and second operative modes respectively.

35

-6-

## DESCRIPTION OF THE PREFERRED EMBODIMENTS

Referring to Figure 1, the plastic tube 10 is produced by extruder 12 and is set to correct diameter by a sizing device, such as a sizing sleeve 13, within a primary cooling spray tank 14. The tube 10 is hauled from the extruder by a first haul-off tractor 16.

The tube 10 then proceeds to a temperature conditioning zone 18, in which the tube is treated to attain a specific temperature profile uniformly around the tube wall, so that the subsequent expansion of the tube causes orientation of the polymer molecules principally in the circumferential direction, thus resulting in enhanced physical properties especially increased resistance to hoop stresses. The tube then enters an expansion zone 20 between a pair of plugs 24 and 26 held inside the tube by a service tube 22 connected back through the extruder head to a thrust restraint (not shown).

The first plug 24 - the upstream plug relative to the direction of travel of the tube 10 - is sized to fit tightly within the unexpanded tube 10. A series of control wheels 25 surrounding the tube circumference push the tube tightly on to the plug 24 so that there is sufficient seal to maintain pressure in the expansion zone. The downstream plug 26 is inflatable so that its diameter can be changed from the unexpanded state to the expanded state in order to start the process.

The plug 26 is preferably as described in our co-pending International Patent Application No. PCT/AU94/00784. The plug is inflated sufficiently to maintain pressure in the expansion zone while allowing some of the expansion fluid to flow past the plug and



-7-

lubricate the plug within the moving tube. The service tube 22 has a pair of concentric tubes, one of which continues forward to carry inflation fluid, for example air, to the downstream plug 26 and the other supplying expansion fluid, preferably hot water, to the upstream plug, which then enters the expansion zone via outlets 27.

Between the two plugs the plastic tube 10 undergoes expansion in the radial direction due to the internal pressure, without external restraint. Towards the downstream end of the expansion zone, there is provided a sizing sleeve 28 or other sizing device and a cooling spray tank 30 for setting the final diameter of the expanded tube 32. This is followed by a second haul-off tractor 34, which may be set at a higher speed than the first tractor if axial orientation of the tube is desired, and cutting equipment (not shown).

Figures 2A and 2B illustrate two modes of operation of the expansion and sizing part of the process. In the first mode, shown in Fig. 2A, the pressure held in the expansion zone behind the inflatable plug is less and the frustroconical shape of the expanding tube more gradual. The tube 10 expands gradually to first contact the sizing sleeve 28 at its entrance or at a point downstream. Adjustment of the pressure in the expansion zone by altering the plug inflation pressure will move the point of first contact between the tube and the sizing sleeve upstream or downstream.

In the second mode, shown in Fig. 2B, the expansion pressure is sufficient to cause inflation of the tube slightly beyond the sizing sleeve diameter. The overexpanded tube is then drawn down to enter the sizing sleeve.

-8-

Providing the inflatable plug 26 is inflated sufficiently for the expanding tube to contact the sizing sleeve in either the two modes discussed above, the final outside diameter of the tube will primarily  
5 be determined by the sizing sleeve, except for some minor variations due to "snap-back" or some slight degree of creep between the sizing sleeve and the downstream plug. However, this is minimal as the cooling of the expanded tube to fix its diameter has  
10 commenced at that point.

Hence, the exact degree of expansion of the inflatable plug has only a slight effect on the final diameter. Instead, the inventors have found that the effect of  
15 under- or over- inflation of the plug is to vary the velocities into and out of the expansion zone, and thus the amount of axial draw which is occurring in the expansion zone and stable running of the process line itself.

20 The average axial draw of the tube is fixed by ratios of the first and second haul-off tractors. Axial draw is introduced both in the expansion zone itself and in the pre-expansion zone between the first haul-off 16  
25 and the upstream plug. Essentially no axial draw is introduced after the expansion zone as the tube has been cooled. Thus, at any time the sum of the axial draw being introduced in the expansion and pre-expansion zones will be equal to the haul-off  
30 ratio and therefore constant. The inventors have found that it is important both to product consistency and the operation of the process itself to control how much of this occurs in each zone.

35 A number of devices for measuring various parameters of the tube 10 before or during expansion are provided

-9-

for indicating the rate at which the tube material enters and leaves the expansion zone 20.

Means 36 for measuring the diameter of the tube may be  
5 provided in the expansion zone, preferably located  
less than three tube diameters, more preferably less  
than one diameter, downstream from the upstream plug.  
The diameter of the tube at this early stage of  
10 expansion gives a surprisingly accurate correlation to  
the shape of the expansion zone and thus the relative  
velocities, yet provides the information soon enough  
for adequate control.

Over-expansion of the tube may start to draw material  
15 from the upstream side of the upstream plug and hence  
velocity measurement means 38 located just upstream  
can provide information for process control. In  
addition, even slight discrepancies in the long term  
average of the relative velocity away from the set  
20 point can cause variation in the pre-expansion  
diameter which is measured by device 41.

The forward thrust generated by the tube on the sizing  
device 28 may be measured by means 39 and used for  
25 process control, as this measurement is very sensitive  
to variations in the shape of the expansion zone.

In addition to the above, the inventors have found  
that an important factor determining the expansion  
30 behaviour is the wall thickness of the extruded tube  
10, and that this measurement generated by wall  
thickness measuring apparatus 40 located before the  
expansion zone, is useful for feed-forward control of  
the process.

35 An increase in wall thickness entering the expansion  
zone will cause narrowing of the cone as it is

-10-

stronger and so resists the expansion pressure. This in turn drags less upstream material into the expansion zone, reducing the upstream velocity and thus is partly self-correcting in terms of mass flow.

5 However, the inventors have found that this changes the balance of the whole production line. The control system according to the invention detects this change in velocity in to the expansion zone (either directly or indirectly) and increases the expansion pressure.

10 This reverses the dip in upstream velocity, even though this increases the mass flow further.

The axial draw over the whole line is determined by the ratio of the two haul-offs and thus is constant.

15 The invention controls how much of this occurs in the expansion zone and how much upstream. Virtually none occurs after the expanding tube leaves the sizing sleeve 28 as the tube has been fixed by cooling.

20 In practice, the signals from the measuring devices 36, 38, 39, 40 and 41 will be fed to a processor 42. If the signals indicate that the relativity between the velocities into and out of the expansion zone has deviated from the set point for the process, the

25 processor will in turn control the inflation fluid supplied to the inflatable plug 26 through the service tube 22. Thus, for example, if early diameter detector 36 signals too high a reading or if the velocity measurement from 38 is more than a

30 predetermined amount greater than the speed of the first tractor 16, pressure will be released from the inflatable plug. This in turn will reduce the pressure of expansion fluid retained behind the plug 26, by allowing excess expansion fluid to escape past

35 the inflatable plug.

The inventors have discovered that the relationship

-11-

between the inflation pressure of the plug and pressure drop across the plug is predictable according to the following equation:

5            $P_p = \Delta P + P_d$

where  $P_p$  = Pressure applied to plug

$\Delta P$  = Pressure differential across plug

10

$P_d$  = Pressure to expand plug to diameter  
d without confinement (free expansion  
pressure)

15 While control of the expansion by varying the plug pressure has been found by the inventors to be very convenient and is preferred, it will be appreciated that other control responses may be employed in addition or as alternatives. For example, the  
20 relative velocities into and out of the expansion zone can be controlled more directly by varying the haul-off rate at tractor 34.

The detected properties are preferably used in  
25 combination for control of the process. For example, the thrust on the sizing sleeve and the wall thickness of the unexpanded tube may be used for coarse adjustment while fine adjustments may be made in response to variations in the linear velocity reading  
30 from 38 and the early expansion diameter measurement from 36. A preferred method of combining use of the control parameters is to use variations in the sizing sleeve thrust measurement to vary the control set point for the early expansion diameter.

35

While particular embodiments of this invention have been described, it will be evident to those skilled in

-12-

the art that the present invention may be embodied in other specific forms without departing from the essential characteristics thereof. The present embodiments and examples are therefore to be

5 considered in all respects as illustrative and not restrictive, the scope of the invention being indicated by the appended claims rather than the foregoing description, and all changes which come within the meaning and range of equivalency of the

10 claims are therefore intended to be embraced therein.

15

CLAIMS

1. A method of expanding a tube of plastics material,  
in which a longitudinally travelling tube is  
progressively diametrically expanded by internal fluid  
pressure in an expansion zone between an upstream plug  
5 which fits closely within the bore of the  
substantially unexpanded tube and a downstream plug  
which fits closely within the bore of the tube after  
the expansion step, wherein expansion of the tube is  
controlled in response to one or more parameters which  
10 directly or indirectly indicate variation in the  
relative velocity at which the material is delivered  
to and is removed from the expansion zone.
2. A method according to claim 1 wherein said  
15 parameter comprises a comparison of tube velocity  
upstream and downstream of the expansion zone.
3. A method according to claim 1 wherein said  
parameter comprises velocity of the unexpanded tube  
20 entering the expansion zone.
4. A method according to claim 1 wherein said  
parameter comprises the diameter of the partly  
expanded tube at a point in the expansion zone less  
25 than three pre-expansion tube diameters downstream of  
the upstream plug.
5. A method according to claim 4 wherein said point  
is less than one pre-expansion tube diameter  
30 downstream from the upstream plug.
6. A method according to claim 1 wherein said  
parameter is axial force applied by the expanding tube

-14-

on a sizing device.

7. A method according to claim 1 wherein said  
expansion is controlled by varying the internal fluid  
5 pressure in the expansion zone.

8. A method according to claim 7 wherein said  
expansion is controlled by controlling leakage of  
fluid from the expansion zone past the downstream  
10 plug.

9. A method according to claim 8 wherein said  
downstream plug is inflatable by internal fluid  
pressure of an inflation fluid within the downstream  
15 plug, and said leakage is controlled by varying the  
pressure of said inflation fluid.

20








FIG. 1



## INTERNATIONAL SEARCH REPORT

International Application No.  
PCT/AU 96/00514

**A. CLASSIFICATION OF SUBJECT MATTER**

Int Cl<sup>6</sup>: B29C 55/24, 55/26, 47/90, 47/92//B29L 23:00, B29K 101:12

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

IPC: B29B, B29C, B29D & keywords

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched  
AU: B29C 55/24, 55/26

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)  
DERWENT: (TUBE# OR PIPE# OR CONDUIT#) AND (EXPAND: OR ENLARG:) AND PRESS: AND  
(VELOCIT: OR SPEED: OR MOV:)


**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO, 90/2644, A, (VINIDEX TUBEMAKERS PTY LIMITED) 22 March 1990	1-9
A	US, 5096634, A (GEORGE ARISTOVOULOS PETZETAKIS) 17 March 1992	1-9
A	WO, 93/19924, A (BP CHEMICALS LIMITED) 14 October 1993	1-9

☒ Further documents are listed in the continuation of Box C

☐ See patent family annex

<p>• Special categories of cited documents:</p>	
"A" document defining the general state of the art which is not considered to be of particular relevance	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"E" earlier document but published on or after the international filing date	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"O" document referring to an oral disclosure, use, exhibition or other means	"&" document member of the same patent family
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search 9 September 1996	Date of mailing of the international search report 9 OCT 1996
Name and mailing address of the ISA/AU AUSTRALIAN INDUSTRIAL PROPERTY ORGANISATION PO BOX 200 WODEN ACT 2606 AUSTRALIA Facsimile No.: (06) 285 3929	Authorized officer  A. DAVIES Telephone No.: (06) 283 2072

## PCT/INTERNATIONAL SEARCH REPORT

International Application No.  
PCT/AU 96/00514

C (Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, A	WO, 95/25626, A (WAVIN B.V.) 28 September 1995	1-9
P, A	WO, 95/25627, A (WAVIN B.V.) 28 September 1995	1-9
P, A	WO, 95/25628, A (WAVIN B.V.) 28 September 1995	1-9

# INTERNATIONAL SEARCH REPORT

International Application No.  
PCT/AU 96/00514

This Annex lists the known "A" publication level patent family members relating to the patent documents cited in the above-mentioned international search report. The Australian Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

Patent Document Cited in Search Report		Patent Family Member			
WO	9002644	AU	43282/89		
US	5096634	AU	70136/91	CA	2035802
		FI	910595	JP	5000449
				EP	441142
				PT	96669
WO	9319924	AU	38949/93	GB	9206766
WO	9525626	AU	19620/95	NL	9400451
WO	9525627	AU	19622/95	NL	9400453
WO	9525628	AU	19621/95	NL	9400452
END OF ANNEX					